

# ASHLAR PRODUCT DATA SHEET



## Available Sizes

300x200x8mm  
600x300x10mm

## Samples Service

Tel: +44 (0)1782 524 043  
Fax: +44 (0)1782 577 379  
Email: [samples@johnson-tiles.com](mailto:samples@johnson-tiles.com)

## Technical Helpline

Tel: +44 (0)1782 524 111  
Fax: +44 (0)1782 577 379  
Email: [techadvice@johnson-tiles.com](mailto:techadvice@johnson-tiles.com)

[www.johnson-tiles.com](http://www.johnson-tiles.com)

Recycled Content **Up to 20%**

|                         |                                 |
|-------------------------|---------------------------------|
| Range                   | <b>Ashlar</b>                   |
| Category                | <b>Concrete, Made in the UK</b> |
| Collection              | <b>Select Collection</b>        |
| Short Code              | <b>ALR01A</b>                   |
| Colour                  | <b>Warm Taupe</b>               |
| Finish                  | <b>Matt</b>                     |
| Secondary Finish        | <b>Textured</b>                 |
| Wall Suitability        | <b>Internal Only</b>            |
| Floor Suitability       | -                               |
| Wet Barefoot            | -                               |
| Material                | <b>Glazed Ceramic</b>           |
| Classification          | <b>BIII</b>                     |
| Light Reflectance Value | <b>62.00</b>                    |
| CSV                     | <b>V3</b>                       |

## Physical Properties

| Test / Standard   | Requirement                       | Test Result                     |
|---|-----------------------------------|---------------------------------|
| <b>Length/Width</b><br>EN ISO 10545-2                           | $\pm 0.5\% \leq \pm 2\text{mm}$   | <b><math>\pm 0.25\%</math></b>  |
| <b>Thickness</b><br>EN ISO 10545-2                              | $\pm 10\% \leq \pm 0.5\text{mm}$  | <b><math>\pm 2.5\%</math></b>   |
| <b>Straightness of Sides</b><br>EN ISO 10545-2                  | $\pm 0.3\% \leq \pm 1.5\text{mm}$ | <b><math>\pm 0.15\%</math></b>  |
| <b>Rectangularity</b><br>EN ISO 10545-2                         | $\pm 0.5\% \leq \pm 2\text{mm}$   | <b><math>\pm 0.4\%</math></b>   |
| <b>Surface Flatness</b><br>EN ISO 10545-2                       | $\pm 0.5\% \leq \pm 2\text{mm}$   | <b><math>\pm 0.2\%</math></b>   |
| <b>Water Absorption</b><br>EN ISO 10545-3                       | 10% to 20%                        | <b>15% to 17%</b>               |
| <b>Modulus of Rupture</b><br>EN ISO 10545-4                     | Ave 15N/mm <sup>2</sup>           | <b>25N/mm<sup>2</sup></b>       |
| <b>Frost Resistance</b><br>Not Applicable                       | N/A                               | <b>Not suitable</b>             |
| <b>Chemical Resistance</b><br>EN ISO 10545-13                   | Min Class B                       | <b>Class A-B (better)</b>       |
| <b>Stain Resistance</b><br>EN ISO 10545-14                      | Min Class 3                       | <b>Class 3 (better)</b>         |
| <b>Fire Rating</b>  |                                   | <b>Class A1 Non Combustible</b> |
| <b>Weight/m<sup>2</sup></b><br>Thickness: 8mm<br>Thickness 10mm |                                   | <b>13.74kg<br/>18kg</b>         |

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmstow, Cheshire, SK9 1BU. Registered in England No. 566694. Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of H&R Johnson Tiles Limited and licensed to Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.