## ATRIUM PRODUCT DATA SHEET



	Short Code	ATRMIN
and the second second	Colour	Clay
	Finish	Natural
	Wall Suitability	Internal & External
	Floor Suitability	Internal Only
	Wet Barefoot	-
	Material	Glazed Porcelain
	Classificiation	Bla
	Light Reflectance Value	40.00
	CSV	V3
	PTV (4S)	Wet 25-35 Dry 36+
	PTV (TRL)	-
	R Value	9
43 79	Wet Ramp	-
on-tiles.com	PEI	IV
11	Traffic	Commercial
79		

 $\varnothing$  Recycled Content

Range Category

Collection

Up to 20%

**Concrete**, Floor Tiles

Select Collection

Atrium

est / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.4%
↓ Thickness ↑ EN ISO 10545-2	±5%≤ ± 0.5mm	±5%
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.4%
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%
↓ Surface Flatness   ↑ ↑ EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.15%
Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Class A
Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
Fire Rating Not Applicable	N/A	Class A   FL Non Combustible
kg Weight/m <sup>2</sup> Thickness: 8.5mm Thickness: 10mm		19kg 22kg

## Samples Service

Available Sizes 450x450x8.5mm 592x592x10mm 600x300x8.5mm 888x443x10mm

Tel: +44 (0) | 782 524 043 Fax: +44 (0) | 782 577 379 Email: samples@johnson-tiles.com

## Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, lnadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a line bilip potential. 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, SK91BU, Registed in England No. 566694. Johnson Tiles, Johnson Albulte and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of H&R Johnson Tiles Limited and licensed to Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2021 Johnson Tiles. All rights reserved. JOHNSON TILES

