BUCKINGHAM PRODUCT DATA SHEET





Available Sizes

600x600x9mm 900x450x9mm 1200x600x9mm 600x300x9mm 900x900x9mm 1200x1200x9mm 2700x1200x6mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Recycled Content	Up to 30%	
Range	Buckingham	
Category	Marble, Floor Tiles	
Collection	Absolute Collection	
Short Code	вискзв	
Colour	Grey	
Finish	Soft Bush Hammered	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Porcelain	
Classificiation	Bla	
Light Reflectance Value	29.00	
CSV	V2	
PTV (4S)	Wet 25-35 Dry 36+	
PTV (TRL)	-	
R Value	9	
Wet Ramp	A	
PEI	-	
Traffic	Commercial	

Physi	Physical Properties			
Test	Standard	Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
→	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
$\begin{array}{ c c } \hline \downarrow \\ \hline \uparrow \uparrow \\ \hline \end{array}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥55N/mm²	
©	Abrasion Resistance EN ISO 10545-6	≤175mm³	<109mm³	
	Thermal Shock EN ISO 10545-9	Pass	Pass	
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A	
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5	
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg	Weight/m² Thickness: 9mm		21kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, Sk9 1BU. Registed in England No. 566694. Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of HAR.

