BUCKINGHAM PRODUCT DATA SHEET





Available Sizes

1200x1200x20mm 900x900x20mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

${\cal O}$ Recycled Content	Up to 30%	
Range	Buckingham	
Category	Marble, Floor Tiles, PTV	
	36+ Tiles, 2cm	
Collection	Absolute Collection	
Short Code	BUCK2E	
Colour	Light Grey	
Finish	Grip+ 2cm	
Wall Suitability	Internal & External	
Floor Suitability	Internal & External	
Wet Barefoot	Yes	
Material	Porcelain	
Classificiation	Bla	
Light Reflectance Value	55.00	
CSV	V2	
PTV (4S)	Wet 36+ Dry 36+	
PTV (TRL)	Wet 36+	
R Value	11	
Wet Ramp	С	
PEI	-	
Traffic	Commercial	

Physi	cal Properties		
Test /	Standard	Requirement	Test Result
	Length/Width EN ISO 10545-2	±0.5%≤ ± 2mm	Pass
$\begin{array}{ c c }\hline \downarrow \\ \hline \uparrow \\ \hline \end{array}$	Thickness EN ISO 10545-2	±10%≤ ± 0.5mm	Pass
]+	Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	Pass
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
$\begin{array}{ c c }\hline \downarrow \\ \hline \uparrow \uparrow \\ \end{array}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	10% to 20%	Pass
	Modulus of Rupture EN ISO 10545-4	Ave I5N/mm²	≥25N/mm²
	Thermal Shock EN ISO 10545-9	Pass	Pass
<u>*</u>	Frost Resistance Not Applicable	N/A	Not suitable
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
	Fire Rating		Class A1 Non Combustible
kg	Weight/m² Thickness 6mm		10.68kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the stip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Road, Wilmslow, Cheshire, SK9 IBU. Registed in England No. 566694. Johnson Tiles, Donson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of H&R leading to the station of the stat

