## **BUCKINGHAM** PRODUCT DATA SHEET



Range	<b>.</b>	
	Buckingham	
Category	Marble, Floor Tiles	
Collection	Absolute Collection	
Short Code	BUCK5B	+
Colour	Sand	
Finish	Soft Bush Hammered	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	- <u> </u>
Material	Porcelain	
Classificiation	Bla	
Light Reflectance Value	45.00	N N N N N N N N N N N N N N N N N N N
CSV	V2	
PTV (4S)	Wet 25-35 Dry 36+	*
PTV (TRL)	-	B
R Value	9	
Wet Ramp	Α	
PEI	-	
Traffic	Commercial	kg
	Collection Short Code Colour Finish Wall Suitability Floor Suitability Wet Barefoot Material Classificiation Light Reflectance Value CSV PTV (4S) PTV (4S) PTV (TRL) R Value Wet Ramp PEI	CollectionAbsolute CollectionShort CodeBUCK5BColourSandFinishSoft Bush HammeredWall SuitabilityInternal & ExternalFloor SuitabilityInternal OnlyWet Barefoot-MaterialPorcelainClassificiationBlaLight Reflectance Value45.00CSVV2PTV (4S)Wet 25-35 Dry 36+PTV (TRL)-R Value9Wet RampAPEI-

 $\mathcal{O}$  Recycled Content

Up to 30%

## **Physical Properties** Test / Standard Requirement Test Result Length/Width ±0.6%≤ ± 2mm Pass EN ISO 10545-2 Thickness ±5%≤ ± 0.5mm Pass EN ISO 10545-2 Straightness of Sides ±0.5% ≤ ± 1.5mm Pass EN ISO 10545-2 Rectangularity $\pm 0.5\% \leq \pm 2mm$ Pass EN ISO 10545-2 Surface Flatness ±0.5% ≤ ± 2mm Pass EN ISO 10545-2 Water Absorption ≤0.5% ≤**0**.1% EN ISO 10545-3 Modulus of Rupture ≥35N/mm² ≥55N/mm<sup>2</sup> EN ISO 10545-4 Abrasion Resistance ≤175mm<sup>3</sup> <109mm<sup>3</sup> EN ISO 10545-6 Thermal Shock Pass Pass EN ISO 10545-9 Frost Resistance Resistant Resistant EN ISO 10545-12 **Chemical Resistance** Min Class B Class A EN ISO 10545-13 Stain Resistance Min Class 3 Class 5 EN ISO 10545-14 Class A I FL Non **Fire Rating** N/A Not Applicable Combustible Weight/m<sup>2</sup> Thickness: 9mm 21kg

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant redu the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip p and 36 represents a low slip potential. All figures are accurate at the time of this data sheets creation (2 / 103/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Wilmslow, Cheshire, SKP IBU. Registed in England No. 566694. Johnson Tiles, Johnson Tiles. Empiredemarks and together with Kerastar and product names are the trademark Johnson Tiles. Division of Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.



