CONCRETO PRODUCT DATA SHEET



			-
	Range	Concreto	Length
	Category	Concrete, Floor Tiles, PTV	
		36+ Tiles	Thicknee Thicknee EN ISO
	Collection	Absolute Collection	Straigh
	Short Code	CCR03N	
	Colour	Grey	EN ISO
	Finish	Natural	↓ Surface ↑↑ EN ISO
	Wall Suitability	Internal & External	Water
	Floor Suitability	Internal Only	EN ISO
Available Sizes		-	L Modulu EN ISO
605x305x7.8mm 330x330x7.2mm	Material	Glazed Porcelain	Therma EN ISO
608x608x9.5mm	Classificiation	Bla	
900x450x10mm 455x455x8mm	Light Reflectance Value	38.00	EN ISO
	CSV	V4	EN ISO
	PTV (4S)	Wet 36+ Dry 36+	Stain R
Samples Service	PTV (TRL)	-	EN ISO
Tel: +44 (0) 782 524 043 Fax: +44 (0) 782 577 379	R Value	10	UV Col
Email: samples@johnson-tiles.com	Wet Ramp	A	Fire Ra Not Ap
Technical Helpline Tel: +44 (0)1782 524 111	PEI	IV	kg Weight
Fax: +44 (0) 1782 577 379 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com	Traffic	Commercial	Thickne
www.johnson-tiles.com	_		Thickne Thickne Thickne

 \mathcal{O} Recycled Content

Up to 10%

Physical Properties			
Test / Standard	Requirement	Test Result	
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
Water Absorption EN ISO 10545-3	≤0.5%	Pass	
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass	
Thermal Shock EN ISO 10545-9	Pass	Pass	
Frost Resistance EN ISO 10545-12	Resistant	Resistant	
Chemical Resistance EN ISO 10545-13	Min Class B	Class A	
Stain Resistance EN ISO 10545-14	Min Class 3	Class 5	
UV Colour Resistance		Unaffected by light	
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg Weight/m ² Thickness: 7.2mm Thickness: 7.8mm Thickness: 8mm Thickness: 9.5mm		5.78kg 6.9kg 8.39kg 2 .03kg	
Thickness: 10mm		22.24kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36 represents a low slip potential. All figures are accurate at the time of this data sheets creation (16/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registed in England No. 15600432. © 2024 Johnson Tiles. All rights reserved.

