CONGLOMERATES PRODUCT DATA SHEET

 \mathcal{O} Recycled Content

Range

Category

Collection Short Code Up to 10%

Conglomerates

PTV 36+ Tiles

CON02G

Absolute Collection

Stone, Speckle, Floor Tiles,



	Short Code	CONUZG
	Colour	Almond
	Finish	Grip
	Wall Suitability	Internal & External
	Floor Suitability	Internal & External
Available Sizes	Wet Barefoot	Yes
600x600x10.5mm 1200x600x10.5mm	Material	Un-glazed Porcelain
1200x600x10.5mm	Classificiation	Bla
	Light Reflectance Value	55.00
	CSV	V2
	PTV (4S)	Wet 36+ Dry 36+
Samples Service	PTV (TRL)	Wet 36+
Tel: +44 (0) 782 524 043 Fax: +44 (0) 782 577 379	R Value	11
Email: samples@johnson-tiles.com	Wet Ramp	с
Technical Helpline	PEI	-
Tel: +44 (0)1782 524 111 Fax: +44 (0)1782 577 379 Email: techadvice@johnson-tiles.com	Traffic	Commercial
Linait. techauvice@joinison-tites.com		

Physical Properties Test / Standard	Requirement	Test Result
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
↓ Thickness ↑ EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
◆ Surface Flatness ► N ISO 10545-2	±0.5% ≤ ± 2mm	Pass
Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥45N/mm²
Thermal Shock EN ISO 10545-9	Pass	Pass
Frost Resistance EN ISO 10545-12	Resistant	Resistant
Chemical Resistance EN ISO 10545-13	Min Class B	Class A
Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg Weight/m ² Thickness: 10.5mm		25kg

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant red the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 – 24 represents a lips lip potential. 25 – 35 signifies a moderate slip p and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (21/03/2021). Johnson Tiles is a division of Norcros Group (Holdings) Limited, Ladyfield House, Station Wilmslow, Cheshire, SKP IBU. Registered traded in England no. 566694. Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademark Johnson Tiles. © 2021 Johnson Tiles. All rights reserved.



