DANUBE PRODUCT DATA SHEET



	arnothing Recycled Content	Up to 10%	
	Range	Danube	
	Category	Stone, Speckle, Floor Tiles,	
		PTV 36+ Tiles, 2cm	
	Collection	Absolute Collection	
	Short Code	DAN02E	
	Colour	Beige	
	Finish	Grip+ 2cm	
	Wall Suitability	Internal & External	
	Floor Suitability	Internal & External	
	Wet Barefoot	Yes	
	Material	Glazed Porcelain	
	Classificiation	Bla	
	Light Reflectance Value	42.00	
	CSV	V2	
	PTV (4S)	Wet 36+ Dry 36+	
	PTV (TRL)	Wet 36+	
	R Value	12	
	Wet Ramp	c	
	PEI	IV	
	Traffic	Commercial	

Physical Properties Test / Standard Requirement Test Result				
Test / Star	laara	Requirement	Test Result	
	ngth/Width ISO 10545-2	±0.6%≤ ± 2mm	±0.3%	
	ckness ISO 10545-2	±5%≤ ± 0.5mm	±3%	
- +	aightness of Sides ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.3%	
	stangularity ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
	face Flatness ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
(ter Absorption ISO 10545-3	≤0.5%	≤0.1%	
	dulus of Rupture ISO 10545-4	≥35N/mm²	≥35N/mm²	
7 3	ermal Shock ISO 10545-9	Pass	Pass	
255	st Resistance ISO 10545-12	Resistant	Resistant	
	emical Resistance ISO 10545-13	Min Class B	Class A	
	in Resistance ISO 10545-14	Min Class 3	Pass	
UV	Colour Resistance		Unaffected by light	
	e Rating t Applicable	N/A	Class A I FL Non Combustible	
Thi	ight/m² ckness:9mm ckness:10.5mm		21.78kg 27.32kg	

Samples Service

Available Sizes 592x592x20mm

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (16/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registed in England No. 15600432. © 2024 Johnson Tiles. All rights reserved.



