
## **DANUBE** PRODUCT DATA SHEET



	Range	Danube
	Category	Stone, Speckle, Floor Tiles
		PTV 36+ Tiles
	Collection	Absolute Collection
	Short Code	DAN06N
	Colour	Coral
	Finish	Natural
	Wall Suitability	Internal & External
	Floor Suitability	Internal Only
ailable Sizes	Wet Barefoot	-
2x592x10.5mm	Material	Glazed Porcelain
	Classificiation	Bla
	Light Reflectance Value	53.00
	CSV	V2
	PTV (4S)	Wet 36+ Dry 36+
nples Service	PTV (TRL)	-
: +44 (0)1782 524 043	R Value	10
: +44 (0) 1782 577 379		
ail: samples@johnson-tiles.com	Wet Ramp	Α
hnical Helpline	PEI	IV
: +44 (0)1782 524 111 : +44 (0)1782 577 379	Traffic	Commercial
ail: techadvice@johnson-tiles.com		

Up to 10%

est /	Standard	Requirement	Test Result
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.3%
$\stackrel{\downarrow}{\uparrow}$	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	±3%
-	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.3%
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%
$\downarrow$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%
	<b>Modulus of Rupture</b> EN ISO 10545-4	≥35N/mm²	≥35N/mm²
	Thermal Shock EN ISO 10545-9	Pass	Pass
₩	Frost Resistance EN ISO 10545-12	Resistant	Resistant
5	Chemical Resistance EN ISO 10545-13	Min Class B	Class A
$\mathbb{A}_{\mathbb{A}}$	<b>Stain Resistance</b> EN ISO 10545-14	Min Class 3	Pass
222 2222	UV Colour Resistance		Unaffected by light
	<b>Fire Rating</b> Not Applicable	N/A	Class A I FL Non Combustible
kg	<b>Weight/m²</b> Thickness:9mm Thickness:10.5mm		21.78kg 27.32kg

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potenti and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (16/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registed in Englar No. 15600432. © 2024 Johnson Tiles. All rights reserved.

