STAMFORD

GLAZED PORCELAIN & CERAMIC | FLOOR & WALL TILES

CONCRETE WOOD ABSOLUTE















STAMFORD



This comprehensive collection is comprised of both concrete and wood effect floor and wall tiles offering surface variation. The large-format concrete effect tiles feature realistic detail for pared-back interiors, whilst the wood effect planks add nature-inspired elegance. Also available are geometric décor glazed ceramic wall tiles which evoke Origami effects characteristic of the Serenity trend for a modern aesthetic.












04 www.johnson-tiles.com

Size Formats Sizing & Packing Information



6 - Wall Tiles Only (BIII)		1
		8
®	B	

	Size	Thickness	Finish	Structure	Colour Availability	Pcs / Box	M2 / Box	Kg / Box
	1200x1200mm		N Natural	-	All Colours	I Tile	1.44m²	30.32kg
1 1200x1200mm	9mm	G Grip	-	Bone & Silver Only	I Tile	1.44m²	30.32kg	
2		10.5mm	N Natural	-	All Colours	2 Tiles	1.44m²	35.50kg
Z	I 200x600mm	10.5mm	G Grip	-	All Colours	2 Tiles	1.44m²	35.50kg
3	I 200x200mm	9.5mm	N Natural	-	Wood Colours Only	5 Tiles	1.20m²	27.00kg
4	600x600mm	I 0mm	N Natural	-	All Colours	3 Tiles	1.08m²	24.00kg
5	600x300mm	I 0mm	N Natural	-	All Colours	6 Tiles	1.08m²	23.50kg
		I 0.9mm	M Matt	-	All Colours	3 Tiles	1.44m²	28.35kg
6	1200x400mm	II.2mm	M Matt	Geometric	All Colours	3 Tiles	1.44m²	28.35kg
#	Fitting	Thickness	Finish	Structure	Colour Availability	Pcs / Box	LM / Box	Kg / Box
7	1200x75mm Round Top Skirting	10.5mm	N Natural	-	All Colours	9 Tiles	I 0.80lm	16.98kg
8	600x75mm Round Top Skirting	I 0mm	N Natural	-	All Colours	I5 Tiles	9.00lm	16.98kg

Note: All sizes indicated are metric modular. All sizes shown are nominal. (R) Rectified Edge. For the most up-to-date product availability information for this range, please visit our website - www.johnson-tiles.com





BONE LRV: 53 PEI: IV

Product Codes (Bla): N SMF01N + G SMF01G | Fitting Codes (Bla): N SMF1NS



SILVER LRV: 32 PEI: III

Product Codes (Bla): N SMF02N + G SMF02G | Fitting Codes (Bla): N SMF2NS



PEBBLE LRV: 18 PEI: II

Product Codes (Bla): N SMF03N + G SMF03G | Fitting Codes (Bla): N SMF3NS



CHARCOAL LRV: 19 PEI: III

Product Codes (Bla): N SMF04N + G SMF04G | Fitting Codes (Bla): N SMF4NS



WOOD BONE LRV: 53 PEI: IV
Product Codes (Bla): N SMF0 I W



WOOD SILVER LRV: 38 PEI: III
Product Codes (Bla): N SMF02W



WOOD PEBBLE LRV: 24 PEI: II
Product Codes (BIa): N SMF03W



WOOD CHARCOAL LRV: 16 PEI: III

Product Codes (Bla): N SMF04W



BONE LRV: 61

Product Codes (BIII) Wall Tiles Only: M SMF01M



BONE GEOMETRIC STRUCTURE LRV: 61

Product Codes (BIII) Wall Tiles Only: M SMF0ID




SILVER LRV: 50

Product Codes (BIII) Wall Tiles Only: M SMF02M



SILVER GEOMETRIC STRUCTURE LRV: 50

Product Codes (BIII) Wall Tiles Only: M SMF02D



Specification

Range	Finish	Wall Suitability	Floor Suitability	Wet Barefoot	CSV	Material
Stamford	N Natural	Internal & External	Internal Only	-	V2	Glazed Porcelain (BIa)
	G Grip	Internal & External	Internal & External	Yes	V2	Glazed Porcelain (BIa)
	M Matt	Internal Only	-	-	V2	Glazed Ceramic (BIII)

Floor Values

Finish	Structure	Colour	PTV (4S)	PTV (TRL)	R Value	Wet Ramp	PEI	Traffic
	-	Bone	Dry 36+ Wet 36+	-	RIO	С	IV	Commercial
N Natural	-	Silver & Charcoal	Dry 36+ Wet 36+	-	RI0	С	III	Light Commercial
	-	Pebble	Dry 36+ Wet 36+	-	RIO	С	II	Domestic
	-	Bone	Dry 36+ Wet 36+	Wet 36+	RII	-	IV	Commercial
G Grip	-	Silver & Charcoal	Dry 36+ Wet 36+	Wet 36+	RII	-	III	Light Commercial
	-	Pebble	Dry 36+ Wet 36+	Wet 36+	RII	-	II II	Domestic

Physical Properties - Glazed Porcelain (BIa)

Test & Standard	Requirement	Test Result	Test & Standard	Requirement	Test Result
Length / Width EN ISO 10545 - 2	± 0.6% ≤ ± 2mm	± 0.1 %	Modulus of Rupture EN ISO 10545 - 4	Min. 35N / mm²	Pass
Thickness EN ISO I 0545 − 2	± 5% ≤ ± 0.5mm	± 0.5%	Thermal Shock EN ISO 10545 - 9	Pass	Pass
Straightness of Side EN ISO 10545 - 2	± 0.5% ≤ ± 1.5mm	± 0.22%	Frost Resistance EN ISO 10545 - 12	Resistant	Resistant
Rectangularity EN ISO 10545 - 2	± 0.5% ≤ ± 2mm	± 0.22%	Chemical Resistance EN ISO 10545 - 13	Min. Class B	Class B
Surface Flatness EN ISO 10545 - 2	± 0.5% ≤ ± 2mm	± 0.22%	Stain Resistance EN ISO 10545 - 14	Min. Class 3	Pass
Water Absorption EN ISO 10545 - 3	≤ 0.5%	Pass	Fire Rating	-	Class AlfL Non Combustible
kg Weight / M²	24.66kg 22.3 10.5mm thick 10m	33kg 22.50kg nm thick 9.5mm thick	2 I.06kg 9mm thick		

Physical Properties - Glazed Ceramic (BIII)

Test & Standard	Requirement	Test Result		Test & Standard	Requirement	Test Result
Length / Width EN ISO I 0545 - 2	± 0.5% ≤ ± 2mm	± 0.5%	1 1	Modulus of Rupture EN ISO I 0545 - 4	Min. I5N / mm²	Pass
Thickness EN ISO I 0545 - 2	± 10% ≤ ± 0.5mm	± 0.5mm		Thermal Shock EN ISO I 0545 - 9	Pass	Pass
Straightness of Side EN ISO 10545 - 2	± 0.3% ≤ ± 1.5mm	± 0.07%	1	Frost Resistance EN ISO 0545 - 12		Not Suitable
Rectangularity EN ISO 10545 - 2	± 0.5% ≤ ± 2mm	± 0.07%		Chemical Resistance EN ISO 10545 - 13	Min. Class B	Class A
Surface Flatness EN ISO 10545 - 2	± 0.5% ≤ ± 2mm	± 0.15%	1	Stain Resistance EN ISO 10545 - 14	Min. Class 3	Class 5
Water Absorption EN ISO 10545 - 3	10% to 20%	≥ 10%	1	Fire Rating	-	Class A I Non Combustible
kg Weight / M²		57kg Imm thick				

$\ensuremath{\mathcal{Q}}$ Sustainability Information

Range	Material	EPD	Recycled Content of the Tiles	Recycled Content of the Packaging	Recyclable Content of the Packaging
Stamford	Glazed Porcleian (BIa)	Yes	Up to 40%	Up to 100% (Boxes)	Up to 100% (Boxes)
	Glazed Cermaic (BIII)	Yes	Up to 40%	Up to 100% (Boxes)	Up to 100% (Boxes)

Note: Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. Given this, please refer to our website for the most up-to-date information. The slip resistance properties of a surface can only be maintained with the implementation of an effective regular cleaning and maintenance regime. The frequency of cleaning should be determined by the property manager based on the potential level of surface contaminants. The need for an additional regular cleaning and maintenance regime is further heightened when tiles are used for external floor and wet barefoot applications. Please contact our technical helpline, or visit our website for specification and installtion advice. All glazed porcelain (Bia) and glazed ceramic (Bill) products listed conform to BS EN 14411. CSY: Colour Shade Variation. PTV (4S): Pendulum Test Value - Slider 96. PTV (TRL): Pendulum Test Value - Slider 55. R Value (DIN 51130). Wet Ramp (DIN 51097). PEI: Porcelain Enamel Institute. For a full overview of our environmental credentials please visit www.johnson-tiles.com/about/sustainability. EPD: Environmental Product Declaration.

09 www.johnson-tiles.com

Important Information

During the manufacturing process of ceramic and porcelain tiles, some variation in shade and pattern can occur. Before fixing any tiles; several boxes should be opened and their contents mixed to ensure that size, colour, shade and patterning are acceptable. The tiles shown are quality products and conform to the physical properties listed. For a comprehensive colour, size and finish overview along with full technical and sustainability information for all of the product shown in this product presenter, please visit our website – www.johnson-tiles.com.

- · All sizes shown are metric modular.
- For specific suitability details please contact our technical department.
- Johnson Tiles cannot accept responsibility for tiles that have been fixed.
- Every effort has been made to ensure the accuracy of the information given.
- Johnson Tiles reserves the right to change specification and availability information without prior notice.
- Nothing in these statements does/will affect the statutory rights of the consumer.



All product technical values quoted in this product presenter are supported by laboratory testing from our own and independent ceramic test houses. Johnson Tiles are British Standard registered and all products conform to the standards set in BS EN 14411.

For the reassurance of single-source supply, Johnson Tiles offers a free of charge NBS M40 specification writing service featuring the Norcros Adhesives range of tile fixing products. To find out more or for any questions or queries relating to any tile related technical information featured in this product presenter, please contact our technical advice helpline on +44 (0) 1782 524 111 or email ddunlop@johnson-tiles.com

The colours shown in this sample tile wallet and attached booklet are as accurate as printing processes will allow. Please refer to actual product samples before specifying. Every effort has been made to ensure the accuracy of the information given.

® Johnson Tiles, Johnson, Absolute and Material Lab are registered trademarks and together with Kerastar and product names are the trademarks of H&R Johnson Tiles Limited and licensed to Norcros Group (Holdings) Limited trading as Johnson Tiles. © 2022 Johnson Tiles. All rights reserved.



0 www.johnson-tiles.com

For more information about Stamford or any of our other product ranges simply visit www.johnson-tiles.com | f > 0 p in D

Where To Find & Contact Us

Johnson Tiles Head Office

Harewood Street, Tunstall, Stoke on Trent, Staffordshire, ST6 5JZ, United Kingdom

Tel: +44 (0) 1782 575 575 Email: info@johnson-tiles.com www.johnson-tiles.com

Material Lab Studio

10 Great Titchfield Street, London, WIW 8BB, United Kingdom

Tel: +44 (0)20 7436 8629 Email: info@material-lab.co.uk www.material-lab.co.uk

Johnson Tiles Factory Outlet

Tel: +44 (0) I 782 524 040 Email: foutlet@johnson-tiles.com www.outlet.johnson-tiles.com

Customer Services

Tel: +44 (0) I 782 524 000 Email: sales@johnson-tiles.com

Order A Sample

Tel: +44 (0) 1782 524 043 Email: samples@johnson-tiles.com

Technical Advice

Tel: +44 (0) | 782 524 | | | | Email: ddunlop@johnson-tiles.com JOHNSON - TILES
MADE IN THE UK SINCE 1901